AMENDMENT NO. 2 SEPTEMBER 2017
TO
IS 14968 : 2015 TEXTILES — HIGH DENSITY POLYETHYLENE (HDPE)/POLYPROPYLENE (PP) WOVEN SACKS FOR PACKAGING 50 kg/25 kg SUGAR — SPECIFICATION

(First Revision)

[*Page* 2, *Table* 1, *Sl No.* (i)] — Delete.

[*Page* 2, *Table* 1, *Sl No.* (ii), (viii) *and* (ix)] — Substitute the following for the existing:

Sl No.	**Characteristic**	**Requirement**		**Tolerance**	**Method of Test, Ref to**
		Type I	Type II		
(1)	(2)	(3)	(4)	(5)	(6)
ii)	Dimensions (*see* Notes 1 and 2):				Annex B
	a) Inside length, mm	900	630	+ 20/-10	
	b) Inside width, mm	590	480	+ 20/- 10	
viii)	Elongation at break of fabric, (Ravelled strip method), percent :				IS 1969 (Part 1)
	a) Lengthwise	15 to 25	15 to 25	—	
	b) Widthwise	15 to 25	15 to 25	—	
ix)	Breaking strength of fabric after exposure to UV radiation and weathering, *Min*	50 percent of original value		—	Annex C

(*Page* 5, *clause* **D-1**, *lines* 4 *and* 5) — Substitute ‘590°C’ *for* ‘550°C’.

(*Page* 5, *clause* **D-2.5**, *line* 2) — Substitute ‘590°C’ *for* ‘550°C’.

(*Page* 6, *clause* **D-4.1**, *line* 1) — Substitute ‘590°C’ *for* ‘550°C’.

(*Page* 6, *clause* **D-4.5**, *line* 2) — Substitute ‘590°C’ *for* ‘550°C’.

(TXD 23)

Publication Unit, BIS, New Delhi, India